



BUILDING PRODUCTS OF CANADA CORP.

TECHNICAL DATA SHEET

SATURATED FELT

#15 CSA PERFORATED

DESCRIPTION:

This saturated felt **#15 CSA Perforated** is a uniform flexible felt of organic fibres, impregnated with an asphalt saturant. Perforated by more than 1200 holes per square meter with guide lines on the top surface for alignment.

USES:

This saturated felt **#15 CSA Perforated** is used on Built-Up Roofing Systems.

STORAGE:

Stand rolls upright and protect from the elements. Rolls should not be stored directly on the ground.

PHYSICAL PROPERTIES

Width	914 mm (36 in)
Length	43.8 m (144 ft)
Surface	40.14 m ² (432 ft ²)
Guide lines	Yes
Rolls / Pallet	20

CHARACTERISTICS	UNITS		RESULTS BP		REQUIREMENTS		TEST METHOD
	METRIC	IMPERIAL	METRIC	IMPERIAL	METRIC	IMPERIAL	
Average breaking strength at 23°C (73°F), with fibre grain, min.	kN/m	lbf/in	Pass	Pass	5.2	30	ASTM D146
Average breaking strength at 23°C (73°F), across fibre grain, min.	kN/m	lbf/in	Pass	Pass	2.6	15	ASTM D146
Pliability with a radius of 12.7 mm (1/2 in)	mm	in	Pass	Pass	No crack	No crack	ASTM D146
Moisture at manufacturing	%	%	Pass	Pass	3	3	ASTM D146
Liquid water transmission test			n/a	n/a	n/a	n/a	ASTM D4869
Net mass of saturated felt, min.	g/m ²	lb/100 ft ²	Pass	Pass	548	11.2	ASTM D146
Net mass of saturant min.	g/m ²	lb/100 ft ²	Pass	Pass	288	5.9	ASTM D146
Net mass of desaturated felt, min.	g/m ²	lb/100 ft ²	Pass	Pass	240	4.9	ASTM D146
Saturation min.	%	%	Pass	Pass	120	120	ASTM D146
Saturation efficiency min.	% by wt	% by wt	Pass	Pass	70	70	ASTM D146

APPLICABLE STANDARDS AND CERTIFICATION

CSA A123.3 Type 1
FM Approved